



## Product Data

### Castrol Braycote<sup>®</sup> 602 EF

Grease, Molybdenum Disulfide Compound,  
Rocket Propellant Compatible, Low Temperature

#### QC Lubricants

CAGE CODE 9Y364

7360 Milnor St • Philadelphia, PA 19136

(215) 333-4187 Direct Line

Toll Free **With Extension: (800) 887-2436**

For Technical Assistance **Dial Extension 203** for Stan Jakubowski

For Sales Assistance **Dial Extension 211** for Lu Ann Quinn

[QCLubricants.com](http://QCLubricants.com) for [Braycote Micronic 602 EF Purchase and Information](#)

### Description

Castrol Braycote 602 EF is a smooth, buttery, gray colored NLGI #2 grease. The base fluid (Castrol Brayco<sup>®</sup> 815Z) is a stable perfluorinated polyether with exceptional chemical resistance, extremely low volatility, and a wide temperature service range. The gelling agent is a tetrafluoroethylene telomer. This grease contains molybdenum disulfide. This product is nonflammable, does not use any chlorofluorocarbons (CFC's) during product manufacture, and is in general, chemically inert. It is an excellent lubricant, has good shear stability, and low acute toxicity. Castrol Fluoroclean<sup>™</sup> X100 or Castrol Fluoroclean<sup>™</sup> HE can be used to remove this lubricant. Refer to the data sheets for these products for more information.

### Application

Braycote 602 EF is designed to operate in the presence of fuels, oxidizers, and deep space vacuums. Typical applications include ball and roller bearings, gears, electrical contacts, and as an assembly lubricant for O-rings and elastomers. This grease is highly recommended in applications where temperature extremes and/or low vacuums are routine. Perfluorinated greases, such as this product, exhibit excellent shelf life due to their intrinsic inertness.

### Characteristics

TEST METHOD	DESCRIPTION	RESULT
D 1403	Penetration, 25°C (77°F), mm <sup>-1</sup> Unworked Worked, 60 strokes	268 273
D 2265	Dropping Point, °F (°C)	460 (238)
FTM 321	Oil Separation, % wt 30 hrs, 204°C (400°F) Evaporation Loss, %	10.8 0.12
D 2266	Four-Ball Wear-Test, AWSD @ 167°C, mm 1200 rpm, 40 Kg, 1 hr @ 75°C (167°F) @ 204°C (400°F)	1.15 1.04
BOC	Evaporative weight loss, 72 hrs at 450°F (232°C)	0.22
D 2596	Four-Ball Extreme-Pressure Weld, Kg AWSD @ 600 Kg, mm	800+ 1.85
Spec	Molybdenum Disulfide Content, (Mil-M-7866), % wt	5
D 2512 (MSFC 106)	LOX Impact Sensitivity 1100 mm, 20 drops	Pass

E 595 NASA SP-R-0022A	Vacuum Stability Test 24 hrs, 125°C (257°F), 10 <sup>-6</sup> , torr Total Weight Loss (TML), % wt Volatile Condensable Material (VCM), % wt	0.21 0.04
D 3336	High temperature bearing performance, hours	700+
D 1478	Low temperature torque, gm-cm @ -62°C (-80°F) Starting Running, 1 hr @ -73°C (-100°F) Starting Running, 1 hr	585 228 592 429

## Base Oil Characteristics

D 287	Specific Gravity @ 20°C (68°F) Pounds per gallon @ 20°C (68°F)	1.85 15.4
D 445	Kinematic Viscosity, cSt @ 99°C (210°F) @ 38°C (100°F) @ -54°C (-65°F)	45 148 11,500
D 2270	Viscosity Index	350
D 97	Pour Point, °C (°F)	-72 (-100)
Knudsen	Vapor Pressure, torr @ 20°C (68°F) @ 100°C (212°F) @ 200°C (392°F)	$4 \times 10^{-13}$ $2 \times 10^{-9}$ $2 \times 10^{-6}$

Health, safety and environmental information are provided for this product in the Materials Safety Data Sheet. This gives details of potential hazards, precautions and First Aid measures, together with environmental effects and disposal of used products. Castrol will not accept liability if the product is used other than in the manner or with the precautions or for the purpose(s) specified. Before using the product other than directed, please contact Castrol for consultation.

## Additional Information

### Temperature Range

-80°C to 204°C (-112°F to 400°F)

## Limitations

Braycote 602 EF is compatible with most commonly utilized materials, plastics, and elastomers. It may be adversely affected by Lewis Acid catalysts such as aluminum chloride, at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium or titanium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to grease application to insure proper lubrication. This product is not recommended for use in applications under high vacuum with loads exceeding 100,000 psi for extended periods of time.

## Packaging

Braycote 602 EF is packaged in 2 oz (AVDP) and 4 oz disposable plastic syringes and 1 pound jars.

Castrol Braycote 602 EF  
07.15.2005, Version Number 2.0  
Braycote 602 EF and the Castrol logo are trademarks of Castrol Limited.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol Ltd products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563  
Tel: (877) 641 1600 Fax: (877) 648 9801

[www.castrol.com/industrial](http://www.castrol.com/industrial)

## QC Lubricants

**CAGE CODE 9Y364**

**7360 Milnor St • Philadelphia, PA 19136**

**(215) 333-4187 Direct Line**

**Toll Free With Extension: (800) 887-2436**

**For Technical Assistance Dial Extension 203 for Stan Jakubowski**

**For Sales Assistance Dial Extension 211 for Lu Ann Quinn**

**[QCLubricants.com](http://QCLubricants.com) for [Braycote Micronic 602 EF Purchase and Information](#)**